



Français

1 of 1

Images

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(11) WO 2004/059396

(13) A1

(21) PCT/JP2003/016064

(22) 16 December 2003 (16.12.2003)

(25) Japanese

(26) Japanese

(30) 2002-374941

25 December 2002

JP

(25.12.2002)

(43) 15 July 2004 (15.07.2004)

(51)⁷ G03G 9/087, 9/097, 15/20, C08G 63/127

(54) POLYESTER RESIN FOR TONER, TONER FOR DEVELOPING ELECTROSTATIC CHARGE IMAGE AND METHOD FOR FORMING IMAGE

(71) TOYO INK MANUFACTURING CO., LTD. [JP/JP]; 3-13, Kyobashi 2-chome, Chuo-ku, Tokyo 104-8377 (JP). JAPAN U-PICA COMPANY, LTD. [JP/JP]; 1-1, Uchisaiwaicho 2-chome, Chiyoda-ku, Tokyo 100-0011 (JP).

(71) 東洋インキ製造株式会社 (TOYO INK MANUFACTURING CO.,LTD.) [JP/JP]; 〒104-8377 東京都 中央区 京橋2丁目3番13号 Tokyo (JP). 日本ユピカ株式会社 (JAPAN U-PICA COMPANY,LTD.) [JP/JP]; 〒100-0011 東京都 千代田区 内幸町2丁目1番1号 Tokyo (JP).

(72) NAKANISHI, Yasushi [JP/JP]; c/o TOYO INK MANUFACTURING CO., LTD.,

(75) 3-13, Kyobashi 2-chome, Chuo-ku, Tokyo 104-8377 (JP). IEMURA, Hirofumi [JP/JP]; c/o TOYO INK MANUFACTURING CO., LTD., 3-13, Kyobashi 2-chome, Chuo-ku, Tokyo 104-8377 (JP). YAMANE, Akira [JP/JP]; c/o JAPAN U-PICA COMPANY, LTD., 1-1, Uchisaiwaicho 2-chome, Chiyoda-ku, Tokyo 100-0011 (JP). ONOSE, Yoshinori [JP/JP]; c/o JAPAN U-PICA COMPANY, LTD., 1-1, Uchisaiwaicho 2-chome, Chiyoda-ku, Tokyo 100-0011 (JP).

(72) 中西 靖 (NAKANISHI,Yasushi) [JP/JP]; 〒104-8377 東京都 中央区 京橋2

(75) 丁目3番13号 東洋インキ製造株式会社内 Tokyo (JP). 家村 浩文 (IEMURA,Hirofumi) [JP/JP]; 〒104-8377 東京都 中央区 京橋2丁目3番13号 東洋インキ製造株式会社内 Tokyo (JP). 山根 晃 (YAMANE,Akira) [JP/JP]; 〒100-0011 東京都 千代田区 内幸町2丁目1番1号 日本ユピカ株式会社内 Tokyo (JP). 小野瀬 芳則 (ONOSE,Yoshinori) [JP/JP]; 〒100-0011 東京都 千代田区 内幸町2丁目1番1号 日本ユピカ株式会社内 Tokyo (JP).

(74) KANAO, Hiroki, et al; Mutsumi International Patent Bureau Chiyada Office, Bandai Bldg. 2nd Floor, 10-14, Kandaawajicho 2-chome, Chiyoda-ku, Tokyo 101-0063 (JP).

(74) 鐘尾 宏紀 (KANAO,Hiroki), et al; 〒101-0063 東京都 千代田区 神田淡路町 2丁目10番14号 ばんだいビル2階 むつみ国際特許事務所 千代田オフィス Tokyo (JP).

(81) CN, KR, US

(84) European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR)

For information on time limits for entry into the national phase please click here

Published

- *with international search report*
- *before the expiration of the time limit for amending the claims and before the claims are republished in the event of receipt of amendments*

(57) A polyester resin for a toner, which is produced by using (1) a disproportionated rosin and (2) terephthalic acid and/or isophthalic acid, as an acid component, (3) a glycidyl ester of a tertiary fatty acid and (4) an aliphatic diol having two to ten carbon atoms, as an alcohol component, and a three or more-valent polycarboxylic acid and/or a three or more-valent polyol, as a crosslinking component, wherein the mole ratio of the acid component (1) to the acid component (2) [(1)/(2)] is 0.2 to 0.6, and the mole ratio of the alcohol component (3) to the acid component (4) [(3)/(4)] is 0.05 to 0.4; a toner for developing an electrostatic charge image which comprises the polyester resin for a toner (a binding resin), a coloring agent and a charge controlling agent; and a method for forming an image using the a toner for developing an electrostatic charge image.



Français 
1 of 1